

// 757AA



EVOLUTION

灰浆 40 bar (600 psi)

内胶层: 黑色导电NR – 耐磨损

加强层: 高强度纤维线

外胶层: 黑色导电SBR/NR – 耐磨损、耐臭氧 – 表皮刺孔

应用: 灰浆喷射

常规运行温度范围: -30° C +80° C (-22° F +176° F)

↔		↔		↓	↔	↔		↔	↔	↔	↔	
mm	in	mm	in	bar	psi	bar	psi	mm	in	%	kg/m	lb/ft
25,0	1"	38,00	1,50	40	600	100	1.500				0,640	0,44
32,0	1 1/4"	46,00	1,81	40	600	100	1.500				0,860	0,58
35,0	1 3/8"	49,00	1,93	40	600	100	1.500				0,870	0,59
38,0	1 1/2"	54,00	2,13	40	600	100	1.500				1,110	0,75
51,0	2"	67,00	2,64	40	600	100	1.500				1,820	1,23